

Lotrène® Q2018C

LINEAR LOW DENSITY POLYETHYLENE

Linear Low Density Polyethylene (LLDPE)

DESCRIPTION AND USE

Lotrène® Q2018C is a Linear Low Density Polyethylene resin produced in a gas phase reactor using butene (C4) co-monomer.

Lotrène® Q2018C can be processed at optimal output rates with moderate extrusion pressure, good web stability and gauge control on cast film machines designed for LLDPE. Lotrène® Q2018C can advantageously be blended with LDPE or other PE resins used in cast film mono extrusion or co-extrusion to improve film properties.

Lotrène® Q2018C is for melt index 2.0 cast stretch film market. It is suited for many applications in the field of consumer, industrial, food or hygiene packaging as well as non-packaging applications like agricultural films e.g. mulching films.

ADDITIVE PACKAGE

Product	Slip (Erucamide)	Antiblock	Processing aid	Thermal Stabilizers
Q2018C	no	no	no	Yes (cast film)

CHARACTERISTICS

Property	Method	Unit	Value
Density (*)	ASTM D-792	g/cm ³	0.918
Melt Flow Rate (190°C/2.16 kg)	ASTM D-1238	g/10 min	2.0
Melting temperature	Internal	°C	121
Vicat temperature	ASTM D-1525 (A120)	°C	100

(* density of base resin)

CAST FILM PROPERTIES

Properties	Method	Unit	Value (*)
Tensile Strength at Yield MD/TD	ASTM D-882	MPa	9.7 / 9.6
Tensile Strength at Break MD/TD	ASTM D-882	MPa	37 / 23
Elongation at Break MD/TD	ASTM D-882	%	330 / 670
Elmendorf tear resistance MD/TD	ASTM D-1922	N/mm	12 / 193
Secant modulus at 1% MD/TD	ASTM D-882	MPa	165 / 170
Dart test, F50	ASTM D-1709	g	35
Puncture force	ASTM D5748	N	25
Puncture energy	ASTM D5748	J	1.6
Haze	ASTM D-1003	%	1.8
Gloss @ 45°	ASTM D2457		92

The above properties are measured 20 µm films produced on a cast film line under the following parameters: 30 mm screw, L/D = 30:1, die length = 600 mm, die gap = 0.8 mm, line speed = 50 m/min, temperature setting = 180-230°C. Melt temperature 250°C. Chill roll temperature: 25°C.

Processing

Lotrène® Q2018C is typically extruded at a melt temperatures between 220 and 250°C.

Lotrène® Q2018C can be cast in the following conditions on machine designed for LLDPE:

- Extrusion temperature: 180 to 270°C
- Line speed: > 400 m/min
- Die gap: > 0.8 mm

An excellent blending ability of LOTRÈNE Q2018C with LDPE and HDPE and mLLDPE was observed.

HANDLING & STORAGE

Polyethylene products should be stored in their original packaging or in clean appropriate silos.

The products should be stored in a dry and well-ventilated area and should not be exposed to direct sunlight and/or heat in any form since this may adversely affect their properties.

As a general rule, our products should not be stored for more than three months from receipt date.

SAFETY

Under normal conditions Lotrène® products do not present a toxic hazard through skin contact or inhalation.

For detailed information please refer to the Safety Data Sheet.

FOOD CONTACT & REACH

Lotrène® polyethylene products manufactured by Qatofin Company Ltd (Qatofin) comply with US, EU and other food contact legislations. Limitations may apply. Please contact your Muntajat representative for detailed compliance certificates.

All Qatofin Lotrène products are complying with REACH Regulation 1907/2006/EC. The aims of this regulation are to improve the protection of human health and the environment through better and earlier identification of the intrinsic properties of chemical substances.

NOT SUITABLE FOR PHARMACEUTICAL OR MEDICAL APPLICATIONS

Lotrène® products are not suitable for pharmaceutical or medical applications.

TECHNICAL DISCLAIMER

The values reported in this technical data sheet are the results of tests carried out in accordance with standard test procedures in a laboratory environment. Actual properties may vary depending on batch and extrusion conditions. Therefore, these values should not be used for specification purposes.

Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question, and is further advised against relying on the information contained herein as it may relate to any specific use or application.

It is the ultimate responsibility of the user to ensure that the product is suitable for, and the information is applicable to, the user's specific application. Muntajat does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, expressed or implied, or allegedly arising from any usage of any trade or from any course of dealing, in connection with the use of the information contained herein or the product itself.

The user expressly assumes all risks and liabilities, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Trademarks may not be used in any manner other than expressly authorized in a written agreement and no trademark or license rights of any kind are granted hereunder, by implication or otherwise.



منتجات
Muntajat

www.muntajat.qa

Qatar Chemical and Petrochemical Marketing and Distribution Company (Muntajat) Q.J.S.C.

Products that enrich the world | Chemicals | Polymers | Fertilisers

